

	Corzan CPVC	Vintec Clear	Vintec I	Vintec II
<b>Physical</b>				
Density (g/cm <sup>3</sup> )	1.47	1.4	1.42	1.35
Absorption	0.03	<0.07	.15-.3	0.16
Hardness, Shore D	-	80	89	85
Rockwell Hardness (R Scale)	116	115	115	106
Cell Class	24446-B	-	12454-B	16444-D
<b>Mechanical</b>				
Tensile Strength @ Yield (psi)	7300	426,000	411000	396,000
Flexural Strength	14,300	-	-	-
Yield Strength (psi)	-	7,500	12800	7,400
Flexural Modulus (psi)	361,00	480,000	481000	400,000
Yield Strength (psi)	-	12,000	12800	10,000
Compressive Strength	10,100	-	-	-
Compressive Modulus	196,000	-	-	-
Notched Izod Impact (ft-lb/in)	9	0.9	1	18
<b>Thermal</b>				
Vicat Softening Point (°C)	198	82/179	83/181	83/181
Heat Deflection Temperature @ 66 psi (°C)	-	74/165	82/179	82/179
Heat Deflection Temp (264 psi) (°C/°F)	-	86/154	80/176	80/176
Coefficient of Linear Thermal Expansion (ln./ln.°C)	3.86x10 <sup>-5</sup>	6.7 x 10 <sup>-5</sup>	5.8 x 10 <sup>-5</sup>	6.3 x 10 <sup>-5</sup>
Coefficient of Linear Expansion (in/in/°F)	-	3.7 x 10 <sup>-5</sup>	3.2 x 10 <sup>-5</sup>	3.5 x 10 <sup>-5</sup>
Thermal Conductivity (W/mK)	0.95	-	-	-
<b>Flammability Ratings</b>				
Flame Spread Index	15	Class 1	20	15
Flammability	0.062"	0	-	0
Flammability	-	Self Extinguishing	-	Self Extinguishing
Vertical Burn Test	-	-	5-V	-
Foam Fire Test	-	-	Passed / Classified	-
Limiting Oxygen Index	60%	-	-	-
<b>Chemical</b>				
Chemical Resistance	-	Class B	Class B	Class D
<b>Electrical</b>				
Electrical Volume Resistivity (Ohm/cm)	3.4x10 <sup>15</sup>	6.0 x 10 <sup>-5</sup>	5.4 x 10 <sup>15</sup>	6.0 x 10 <sup>15</sup>
Dielectric Constant (60 Hz)	3.7	-	3.9	3.03
Power Factor	0.01%	-	-	-
Dissipation Factor (60 Hz)	-	-	0.0096	0.0083
Loss Index (60 Hz)	-	-	0.03	0.025
Dielectric Strength (Volts / mil)	1250	-	544	645



801 Corey Street, Scranton, PA 18505

Phone: 1.800.235.8320

Fax: 1.800.858.9266

Website: [www.vycomplastics.com](http://www.vycomplastics.com)

Physical properties of plastic sheeting are represented as "Typical". Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty expressed or implied. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use may vary and are beyond the control of Vycom; therefore, Vycom disclaims any liability incurred as a result of the use of this product in accordance with the data contained in our physical property charts. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use the products in such a manner as to infringe any patent, domestic or foreign.

The "Typical" properties of our plastic sheet cannot be automatically used when engineering finished components; and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use!

	<b>Protec HP</b>	<b>Protec CoPP</b>	<b>Hitec HDPE</b>
<b>Physical</b>			
Density (g/cm <sup>3</sup> )	0.9	0.9	0.960 +
Absorption	Max.01%	Max.0.01%	Max 0.01%
Hardness, Shore D	78	72	69
<b>Mechanical</b>			
Tensile Strength @ Yield (psi)	4,900	3,500	4,600
Flexural Modulus (psi)	190,000	145,000	225,000
Notched Izod Impact (ft-lb/in)	0.9	17	120
Elongation at Yeild (%)	9	10	>600
<b>Thermal</b>			
Vicat Softening Point (°C)	305	298	129
Heat Deflection Temperature @ 66 psi (°C)	210	86	82
Coefficient of Linear Thermal Expansion (In./In.°C)	6.5x10 <sup>-5</sup>	6.5x10 <sup>-5</sup>	6 x 10 <sup>-5</sup>
Maximum Service Temperature, Air (°C)	180	180	180 F
Low Temperature Brittleness F <sub>50</sub>	-	-	<-76
Melt Index (g/cm <sup>3</sup> )	0.5	0.5	0.8
<b>Flammability Ratings</b>			
Flammability Rating	UL94 HB	UL94 HB	UL94 HB
<b>Chemical</b>			
Compliances (VO)	FDA, USDA, NSF* ( natural only)	FDA, USDA, NSF* ( natural only)	FDA, USDA, NSF*

Effective Date: 1/1/2016


 801 Corey Street, Scranton, PA 18505  
 Phone: 1.800.235.8320  
 Fax: 1.800.858.9266  
 Website: [www.vycomplastics.com](http://www.vycomplastics.com)

Physical properties of plastic sheeting are represented as "Typical". Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty expressed or implied. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use may vary and are beyond the control of Vycom; therefore, Vycom disclaims any liability incurred as a result of the use of this product in accordance with the data contained in our physical property charts. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use the products in such a manner as to infringe any patent, domestic or foreign.

The "Typical" properties of our plastic sheet cannot be automatically used when engineering finished components; and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use!