

## FLAMETEC™ THERMAX™ XL PVC (FM 4910 LISTED PVC MATERIAL)

TYPICAL PHYSICAL PROPERTIES	UNITS OF MEASURE	VALUE	ASTM METHOD
<b>Physical</b>			
Density	g/cm <sup>3</sup>	1.53	D 792
Water Absorption	%	0.10	D 570
Hardness	Shore D	85	D 2240
Cell Class	-	12354	D 1784
<b>Mechanical</b>			
Tensile Strength @ Yield	psi	6,600	D 638
Tensile Modulus	psi	436,800	D 638
Notched Izod Impact	ft-lb/in	1.2	D 256
Flexural Strength @ Yield	psi	12,000	D 790
Flexural Modulus	psi	445,000	D 790
<b>Thermal</b>			
Heat Deflection Temperature @ 66 psi	°F	166	D 648
Heat Deflection Temperature @ 264 psi	°F	159	D 648
Vicat Softening Point	°F	171	D 1525
Coefficient of Linear Expansion	in/in/°F	3.4 x 10 <sup>-5</sup>	D 696
<b>Flammability</b>			
FM Global (Factory Mutual)	FM-4910 <sup>D+</sup>	Listed	-
Vertical Burn Test	UL-94*	V-0; 5-VA	-
Flame Spread Index	-	10	E-84

<sup>D</sup> Meets FM-4910 testing Criteria (1/4"-1" Only)

\* FM Listed

\*Meets UL 94 testing Criteria

Physical properties of plastic sheeting are represented as 'Typical'. Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation, and is not to be construed as representation or warranty expressed or implied. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use may vary and are beyond the control of Vycom Corporation; therefore, Vycom Corporation disclaims any liability incurred as a result of the use of this product in accordance with the data contained in our physical property charts. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use the products in such a manner as to infringe any patent, domestic or foreign. The 'Typical' properties of our plastic sheet cannot be automatically used when engineering finished components, and the fabricator or end user is responsible for insuring the suitability of our products for their specific application or end use!